KeyPrint® 3D Drucker Validierung

Status: 31. Januar 2019

MPG

Wir validieren immer mehr Drucker. Sie können Ihren Drucker nicht finden? Rufen Sie uns an!

- ● Validierung abgeschlossen
- □ Validierung in Arbeit

					Biokompatible Resine Klasse 1 / 2a CE-zertifiziert	
	KeyModel™	KeyOrthoModel™	KeyCast™	KeyMask™	KeyGuide™	KeySplint Soft™
EvoDent E120 (405 nm)	●	●	●	●	□	□
EvoDent S Series (405 nm)	●	●	●	●	□	□
Asiga® MAX (405 nm)	●	●	●	●	●	□
Miicraft 125 (405 nm)	●	●	●	●	●	●
 **Miicraft Ultra** (405 nm)	●	●	●	●	●	●
Carbon® M2 (405 nm)					□	●
Structo® DentaForm (405 nm)	□	□	□	□	□	□
Rapid Shape® D30 (385 nm)	□	□	□	□	□	□
Ackuretta Diplo (405 nm)	●	●	●	●	●	□
Bego Varseo® S (405 nm)	●	□	●	□	●	□
Bego Varseo® (405 nm)	●	□	●	□	●	□
MoonRay® S100 (405 nm)	●	□	●	□	●	□

*Asiga ist ein eingetragenes Warenzeichen von Zydex Pty, Ltd.
*Varseo and Varseo S ist ein eingetragenes Warenzeichen von BEGO Bremer Goldschlägerei Wilh. Herbst GmbH & Co. KG
*MoonRay ist ein eingetragenes Warenzeichen von SprintRay, Inc.
*Carbon ist ein eingetragenes Warenzeichen von Carbon, Inc.
*Structo ist ein eingetragenes Warenzeichen von Structo Pte., Ltd.
*Rapid Shape ist ein eingetragenes Warenzeichen von Rapid Shape GmbH

Tel. + 49 77 31 91 21 01 | dental.keystoneindustries.com

PRECISION 3D RESINS
keyprint®
by keystone industries

KeyPrint® Post Cure Units

Status: February 17, 2020

	Model	KeyModel®	KeyOrthoModel®	KeyCast®	KeyMask®	KeyGuide®	KeyTray™	KeySplint Soft®
OtoFlash	G171	4000 flashes per side	4000 flashes per side	2000 flashes per side	4000 flashes per side	5000 flashes per side	pending	2000 flashes per side
Uvitron	Intelliray	2 minutes per side	2 minutes per side	1 minute per side	2 minutes per side	2 minutes per side	pending	2 minutes per side
Photopol (with Asiga)	A5408V	40 minutes total	40 minutes total	40 minutes total	pending	40 minutes total	pending	50 minutes total
Meccatronicore (with Asiga)	BB Cure	40 minutes total	40 minutes total	pending	40 minutes total	40 minutes total	pending	pending
Evodent		10 minutes in water	10 minutes in water	10 minutes in water	10 minutes in water	pending	pending	pending
NextDent (3D Systems)	LC-3DPrint Box	30 minutes per side	30 minutes per side	15 minutes per side	30 minutes per side	30 minutes per side	pending	pending
Dymax	5000-EC	4 minutes per side	4 minutes per side	1 minute per side	4 minutes per side	pending	pending	pending
B9 (with Asiga)	Model Cure	3 minutes per side	2 minutes per side	pending	1 minute per side	1 minute per side	pending	pending
SprintRay	PRO	pending	pending	pending	pending	pending	pending	45 minutes total
Dreve	FotoDent Flash	pending	pending	pending	pending	pending	pending	pending
Structo	PCU	pending	pending	pending	pending	pending	pending	pending